



asota

ASOTA Ges.m.b.H.
Schachermayerstr. 22
A-4020 Linz / Austria

2007

EN 14889-2

Polymer fibres for other purpose in concrete and mortar
Polymer: Polypropylene
Class I
Length: 6 mm
Diameter: 32 μm (7 dtex)
Cross section: round
Tenacity: > 315 N/mm² (> 35 cN/tex)
Consistency (dosage 1.8 kg fibres /m³ concrete [C25/30]):
Slump: - 5.0 cm
Compaction: + 0.11
Vebe time: + 10 sec.

(all above data's are mean values)